

PUB-NO: JP02004277759A
DOCUMENT-IDENTIFIER: JP 2004277759 A
TITLE: STEEL WIRE WITH EXCELLENT CORROSION RESISTANCE

PUBN-DATE: October 7, 2004

INVENTOR-INFORMATION:

NAME	COUNTRY
KURODA, TAKESHI	
IBARAKI, NOBUHIKO	
INT-CL (IPC): C22C 38/00; C22C 38/16; C22C 38/50; G02B 6/44	

ABSTRACT:

PROBLEM TO BE SOLVED: To provide a steel wire having excellent corrosion resistance as well as mechanical properties.

SOLUTION: The steel wire has a composition containing 0.3 to 0.85% C, 0.005 to 0.15% Si, 0.2 to 1.2% Mn, 0.08 to 0.5% Cu, 0.002 to 0.1% Al and 0.002 to 0.01% N and also has 700 N/mm² as tensile strength. The steel wire is useful not only as a material for a deformed wire and a reinforcing wire (reinforcing piano wire) for an optical fiber submarine cable but also as a material for a wire rope etc. for use in fishery, ships, etc., utilizing its superior mechanical properties.

COPYRIGHT: (C)2005, JP0&NCIPI